

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>5</sup>:</b> C23C 30/00, B32B 15/01 // C23C 14/16	<b>A1</b>	<b>(11) International Publication Number:</b> WO 94/18359 <b>(43) International Publication Date:</b> 18 August 1994 (18.08.94)
<b>(21) International Application Number:</b> PCT/GB94/00301 <b>(22) International Filing Date:</b> 15 February 1994 (15.02.94) <b>(30) Priority Data:</b> 9302978.3      15 February 1993 (15.02.93)      GB <b>(71) Applicant (for all designated States except US):</b> THE SECRETARY OF STATE FOR DEFENCE IN HER BRITANNIC MAJESTY'S GOVERNMENT OF THE UNITED KINGDOM OF GREAT BRITAIN AND NORTHERN IRELAND [GB/GB]; Defence Research Agency, Farnborough, Hampshire GU14 6TD (GB). <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> DEAKIN, Martin, John [GB/GB]; 99 Dulverton Road, Ruislip, Middlesex HA4 9LE (GB). NICHOLLS, John, Rayment [GB/GB]; 8 The Green, Great Horwood, Buckinghamshire MK17 0RH (GB). <b>(74) Agent:</b> BECKHAM, Robert, William; Intellectual Property Dept., R69 Building, Defence Research Agency, Farnborough, Hampshire GU14 6TD (GB).		<b>(81) Designated States:</b> CA, GB, JP, RU, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> With international search report.
<b>(54) Title:</b> DIFFUSION BARRIER LAYERS		
<b>(57) Abstract</b>		
<p>A method of applying a continuous stable intermetallic diffusion barrier layer to a high temperature metallic article is described. In many instances, protective coatings are incompatible with the material of the substrate to which they are applied. Such incompatibility is overcome in the invention through <i>in situ</i> formation of an intermediate stable diffusion barrier layer by sequential deposition and subsequent reaction of suitable metals to form a continuous intermetallic layer. A conventional overlay coating may then be applied to the intermetallic layer without risk to the underlying substrate. The invention also contemplates creation of unitary diffusion barriers from multi-layer deposits; deposition of plural diffusion barriers, and formation of complete protective systems comprising substrate, diffusion barrier(s) and overlay coating prior to heat treatment <i>in situ</i>.</p>		

*FOR THE PURPOSES OF INFORMATION ONLY*

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

## DIFFUSION BARRIER LAYERS

The present invention relates to protective coatings for metallic articles, and in particular to stable diffusion barrier coatings which can be applied to inhibit the deterioration of substrate materials as a result of interaction with external stimuli.

5

The utility of many materials is limited by their tolerance of operating conditions since, in hostile environments such as extended exposure to high temperatures and temperature cycling of the type found in gas turbine engines, environmental degradation can be very  
10 severe.

Over the years, technology has developed a variety of protective e coatings to extend the operating lifetime and/or the maximum permitted working temperature of many materials. However, the coatings of  
15 choice for particular applications, for example coatings having good oxidation or corrosion resistance, are not necessarily compatible with the substrate material to which they are applied. In many cases there are unfavourable interactions between the material of the substrate and the coating composition, with the result that the physical and  
20 mechanical properties of the substrate are compromised. Deterioration of metallic materials is accelerated at elevated operating temperatures.

Formation of intermetallic protection layers of high temperature  
25 components is known in JP 570155364, where a  $PtAl_2$  discontinuous intermetallic phase of approximately 35-50 $\mu m$  is formed by a diffusion pack aluminising process at a temperature of 1150°C. High temperature materials are defined as those materials capable of operating at temperatures of 500°C or greater. This protection layer does not  
30 afford uniform protection for the substrate material.

There is therefore a need for a uniform coating technique for high temperature components which will allow the best possible coatings for a given purpose to be applied to a particular substrate regardless of the interactions which might otherwise occur between the two.

5

According to the present invention, this is achieved by applying a stable continuous uniform diffusion barrier as an intermediate coating between the protective coating and the surface of the high temperature substrate material. The diffusion barrier serves to inhibit the  
10 breakdown of the protective coating system by minimising coating/substrate interactions, such that efficacy of the protective coating is maintained even though the composition of the coating may be altered by loss through surface oxidation/corrosion. The diffusion barrier also helps to preserve the physical and mechanical properties  
15 of the substrate, by limiting unfavourable interactions.

In particular, the inventive technique relies on the *in situ* formation of a continuous stable diffusion barrier by means of  
20 sequential layering and subsequent reaction treatment of suitable metallic species to produce a diffusion barrier of intermetallic form. This inventive concept extends also to diffusion barriers consisting of multi-intermetallic layers each limiting the diffusion of a specific element (or elements), and is not necessarily limited to the  
25 formation of a single intermetallic diffusion barrier layer of homogeneous structure. By selection of appropriate intermetallic species, interdiffusion of the protective coating through the barrier can be minimised.

30 The invention is a method of producing a continuous stable intermetallic diffusion barrier on a metallic high temperature article, the method comprising the steps of:

depositing at least a first layer of a first metal on the surface of the article;

- 5 depositing at least a second layer of a second metal on the surface of the article to a depth sufficient to provide a predetermined molar ratio of the first and second metals, and

- performing a reaction treatment which causes the first and second  
10 metals to combine to form an intermetallic species.

The term metallic is used to define substrates made of metal, intermetallic or alloy materials.

15

For certain applications, it may be advantageous to use a number of sequential deposition steps to build up the requisite thickness of first and second metals prior to the reaction step.

- 20 As indicated above, it may sometimes be advantageous to deposit a plurality of intermetallic diffusion barriers, each of which serves as a barrier against diffusion by particular species.

- It is also possible to build up a complete protective system  
25 comprising the metallic article substrate, diffusion barrier(s) and overlay coating prior to heat treatment *in situ* of the complete protective system. In this condition, it is important to ensure that the top-most metal of the diffusion barrier precursor has a low interaction with the overlay coating.

30

The reaction treatment step may be carried out prior to or during the normal alloy heat treatment cycle to which the metallic article is subject. Preferably the reaction treatment is a simple heating step which involves raising the deposited metals to a sufficiently high temperature to initiate the exothermic reaction necessary to form the intermetallic species. This may be performed under moderate vacuum to minimise depletion of the second metal layer by atmospheric oxidation.

Alternatively, the reaction treatment could be carried out at high pressure, for example using a hot isostatic pressing technique. Apart from simple heating, the reaction treatment step could also be performed by thermally exciting the first and second metal layers  
5 using a laser beam, plasma treatment, or any other high energy surface treatment.

Preferably the diffusion barrier layer formed by the method of this invention is of a thickness between  $0.1\mu\text{m}$  and  $10\mu\text{m}$ , although  
10 more preferably the barrier layer thickness is between  $0.8\mu\text{m}$  and  $3.0\mu\text{m}$ .

The invention will now be described by way of example with reference to Figure 1 which shows in schematic form the sequence of  
15 steps necessary to carry out the invention.

Referring now to the Figure, step 1 represents the deposition of a first layer of a metal "A" upon the substrate. The thickness  $t_A$  of this first layer is determined by the overall thickness required for  
20 the reacted thermal diffusion barrier coating and the stoichiometric proportion of metal "A" present within that coating.

Step 2 represents the deposition of a second metal "B" over the first layer deposited in step 1. Again, the thickness  $t_B$  of this  
25 second layer is a function of the required thickness for the finished thermal diffusion barrier and the stoichiometric proportion of metal "B" present.

Step 3 represents the reaction treatment step which results in  
30 combination of the two discrete layers of metals "A" and "B" into a single diffusion barrier layer of intermetallic "AB".

Assuming the reacted diffusion barrier layer  $A_xB_y$  is a stoichiometric intermetallic product, in order to obtain the desired  
35 stoichiometry it must contain proportionally  $x$  moles of metal "A" and  $y$  moles of metal "B". If the respective atomic weights ( $M$ ) of the two metals are  $M_A$  and  $M_B$  and their densities ( $p$ ) are  $p_A$  and  $p_B$ , then the ratio of thicknesses  $t_A$  and  $t_B$  should be in the same ratio as:

$$\frac{x.M_A}{P_A} = \frac{y.M_B}{P_B}$$

This relationship assumes that thickness is directly proportional to  
5 volume. It further assumes that little or no depletion of either  
layer occurs due to solid/gas or solid/solid interactions. Where such  
depletion occurs to an appreciable degree, appropriate adjustments  
must be made to the relative thicknesses of the respective layer or  
layers.

10

#### Example 1

The above technique has been successfully carried out on a  
substrate of commercially available IMI834 titanium alloy. In this  
case, a diffusion barrier was required to serve as an intermediate  
15 layer between the substrate and an oxidation resistant coating. The  
purpose of the oxidation resistant coating was to inhibit the ingress  
of oxygen, thereby limiting the formation of a brittle  $\alpha$ -case layer  
which would otherwise severely reduce the mechanical properties of the  
titanium substrate.

20

The sequence of steps outlined above was employed to form an  
intermetallic  $PtAl_2$  layer from the reaction of sequentially applied Pt  
and Al layers using an R.F. biased D.C. sputtering route.

25 In order to minimise potential solid/solid interactions between  
the substrate material and the first metal "A", particularly in view  
of the high diffusivity of aluminium in titanium, the relatively slow  
diffusing Pt layer was deposited first. This was followed by  
deposition of the required thickness of Al in accordance with the  
30 ratio:

$$\frac{M_{Pt}}{p_{Pt}} 2 \left( \frac{M_{Al}}{p_{Al}} \right)$$

(remembering that for  $PtAl_2$ ,  $x = 1$  and  $y = 2$ ).

5

Depletion of the outer aluminium layer due to atmospheric oxidation was prevented by carrying out the reaction treatment in a moderate vacuum of roughly  $2.0 \times 10^{-5}$  bar. The reaction treatment in this instance consisted of heating for a period of 2 hours at a temperature of  $750^\circ\text{C}$ . X-ray diffraction analysis of the surface of the diffusion barrier coating confirmed that the desired  $PtAl_2$  crystal morphology had been obtained.

The continuous  $PtAl_2$  intermetallic layer thus formed was then overlay-coated with an 80/20 Ni/Cr oxidation resistant layer. An oxidative heat treatment for 100 hours in air at  $700^\circ\text{C}$  subsequently demonstrated the complete effectiveness of the  $PtAl_2$  layer as a diffusion barrier for nickel. Moreover, etching of the substrate surface revealed no evidence of  $\alpha$ -case formation, confirming the efficacy of the Ni/Cr layer as a barrier to oxidation.

Other intermetallics formed as diffusion barriers on IMI834 substrate are TiAl and  $(PtTi_3 + TiAl)$ . Nickel based substrates have also been subjected to the method of this invention, with each of NiCr, NiCrAl, NiAl and Ni having a diffusion barrier of  $PtAl_2$ .

Following diffusion barrier formation on the NiCr and NiAl substrates and application of an overlay coating system, each specimen was subjected to oxidative heat treatment for 80 minutes at  $1050^\circ\text{C}$  and also for 40 minutes at  $1150^\circ\text{C}$ . The  $(PtTi_3 + TiAl)$  diffusion barrier on a substrate of IMI834 was subjected to an oxidative heat treatment of  $700^\circ\text{C}$  for 100 hours. Each of the treatments demonstrated the efficacy of the respective diffusion barrier layers.



Titanium aluminite alloys formed the substrate for intermetallic diffusion barrier layers of  $\text{PtAl}_2$  and also  $\text{TiAl}$ .

The table below summarizes typical diffusion barrier formation for particular substrate materials, with associated typical thickness of diffusion barrier layers and also the efficacy testing conditions.

	Substrate	Diff. Barrier	Thickness range (total) $\mu\text{m}$	Stable exposure conditions
10	IMI 834	$\text{PtAl}_2$	0.7 - 3.2	Up to 100 hrs at 700°C
15	IMI 834	$\text{TiAl}$	1.9	-
	IMI 834	$(\text{PtTi}_3 + \text{TiAl})$	3.0	100 hrs at 700°C
20	$a_2$	$\text{PtAl}_2$	0.6 - 1.8	
	$a_2$	$\text{TiAl}$	1.9	
	NiCr	$\text{PtAl}_2$	1.8 - 4.0	80 mins/1050°C & 40 mins/1150°C
25	NiCrAl	$\text{PtAl}_2$	1.8 - 4.0	
	NiAl	$\text{PtAl}_2$	1.8 - 4.0	80 mins/1050°C & 40 mins/1150°C
30	Ni	$\text{PtAl}_2$	1.8 - 4.0	

From the examples it can be seen that a number of diffusion barrier intermetallics can be used for differing substrates. It will be understood that alternative oxidation resistant overlay coatings could have been used. It will also be appreciated that suitable  
5 overlay coatings need not be confined to those imparting oxidation resistance.

## CLAIMS

1. A method of producing a continuous stable intermetallic diffusion barrier on a metallic high temperature article, the method comprising the steps of:

depositing at least a first layer of a first metal on the surface of the article;

depositing at least a second layer of a second metal on the surface of the article to a depth sufficient to provide a predetermined molar ratio of the first and second metals, and

performing a reaction treatment which causes the first and second metals to combine to form an intermetallic species.

2. A method as claimed in claim 1 wherein a number of sequential deposition steps is employed to build up the requisite thickness of first and second metals prior to the reaction step.

3. A method as claimed in claim 1 or claim 2 wherein a plurality of sequential diffusion barriers of differing compositions is deposited to serve as barriers against diffusion by a variety of species.

4. A method as claimed in any preceding claim wherein the reaction treatment comprises heating the deposited layers to a temperature sufficient to effect exothermic reaction between the constituent metals of the or each diffusion barrier precursor.

5. A method as claimed in any preceding claim wherein the reaction treatment comprises thermal excitation of the deposited layers by high energy surface treatment such as laser beam or plasma treatment.


6. A method as claimed in any preceding claim wherein an overlay coating is applied to the outermost layer of the diffusion barrier or barriers prior to the reaction treatment step to form part of a complete protection system comprising the metallic article substrate, diffusion barrier(s) and overlay coating, which complete protection system is reaction treated *in situ*.

7. A method as claimed in any preceding claim wherein the reaction treatment step is carried out at non-ambient pressure.

8. A diffusion barrier or barriers produced by the method of any preceding claims having a total thickness of between 0.1 $\mu$ m and 10 $\mu$ m.

9. A diffusion barrier or barriers as claimed in claim 8 having a total thickness of between 0.8 $\mu$ m and 3.0 $\mu$ m.

Fig.1



$t_A$  = THICKNESS OF LAYER "A"  
 $t_B$  = THICKNESS OF LAYER "B"

# INTERNATIONAL SEARCH REPORT

International application No.

PCT/GB 94/00301

## A. CLASSIFICATION OF SUBJECT MATTER

IPC5: C23C 30/00, B32B 15/01 // C23C 14/16

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC5: B32B, C23C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

DIALOG, WPI, CLAIMS

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE, A, 1900273 (E.I. DU PONT DE NEMOURS AND COMPANY), 21 August 1969 (21.08.69), page 5, line 1 - line 38 --	1,4
A	JP, A, 4-21756 (TOYOTA MOTOR CORP) 24 January 1992 & Patent Abstracts of Japan Vol.16, No 180 (C-935), abstract of JP 4-21756, publ. 92-01-24 --	1,4
A		1,4

☒ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

\* Special categories of cited documents

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*B\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

\*&\* document member of the same patent family

Date of the actual completion of the international search

3 May 1994

Date of mailing of the international search report

25.05.94

Name and mailing address of the International Searching Authority/Authorized officer



European Patent Office, P.B. 5818 Patentlaan 2  
NL-2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

BENGT CHRISTENSSON

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/GB 94/00301

## C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	Dialog Information Services, File 351, JP 57155364, A, 820925, 8244 (Basic), World Patent Index 81-93, Dialog accession no. 003545866, WPI accession no. 82-93861E/44, HITACHI KK: "Heat-resistant alloy for use e.g. in gas turbines and jet engine having platinum and aluminium outer layers subjected to diffusion treatment to eliminate cpd. phase", & JP 57155364, A, 820925	1,4
A	---	1,4
A	WO, A1, 8809396 (THE SECRETARY OF STATE FOR DEFENCE IN HER BRITANNIC MAJESTY'S GOVERNMENT OF THE UNITED KINGDOM OF GREAT BRITAIN AND NORTHERN IRELAND), 1 December 1988 (01.12.88), page 1, line 1 - line 7; page 4, line 30 - line 35	1,4
A	US, A, 4399199 (IAN R. MCGILL ET AL), 16 August 1983 (16.08.83), page 1, line 10 - line 16; page 1, line 29 - line 50	1,4
	-----	

S 35470

**INTERNATIONAL SEARCH REPORT**  
Information on patent family members

16/04/94

International application No.  
PCT/GB 94/00301

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE-A- 1900273	21/08/69	BE-A- 726397	16/06/69
		FR-A- 2000014	29/08/69
		GB-A- 1248794	06/10/71
		NL-A- 6900122	07/07/69
		US-A- 3583062	08/06/71
		US-A- 3798010	19/03/74
WO-A1- 8809396	01/12/88	DE-A- 3864261	19/09/91
		EP-A,B- 0358685	21/03/90
		JP-T- 2504289	06/12/90
		US-A- 4946749	07/08/90
US-A- 4399199	16/08/83	CA-A- 1145626	03/05/83
		DE-A- 3003520	14/08/80
		FR-A,B- 2447980	29/08/80
		GB-A,B- 2041246	10/09/80
		JP-A- 55130756	09/10/80
		SE-A- 8000480	02/08/80